



ISOPRENE CC

Polymeric retanning agent, isoprenic, with good filling properties.

COMMERCIAL LABORATORY

ASA Industria Química Ltda

453, Adolfo Otto Koch St.

Neighborhood: Das Rosas

City: Estância Velha

State: Rio Grande do Sul

Zip Code: 93602-100

Phone: +55 (51) 3561-9736 / +55 (51) 997-265-261 – Mr. Aldo Stella

E-mail: asachemical@gmail.com

aldost2001@gmail.com

CHEMISTRY FEATURE

Aspect:	Viscous
Color:	Lightly pink
Light fastness:	Very Good
Acid stability:	Good
Electrolytes stability:	Good
Concentration:	12% +/- 2%
pH (10%):	5,5 +/- 0,5
Charge:	Anionic

PRODUCT CHARACTERISTICS

ISOPRENE CC has an excellent filling effect with great firmness and grain appearance. The product is developed for retanning of skins and leathers with loose structure. It is usually applied with synthetics or vegetables retanning agents or based resin. If combined with other polymer based aids, each product should be diluted and added separately to the boiler.

ISOPRENE CC is stable in production baths with a pH above 3.5, and it's not reactive with alkaline earth salts. It does not affect water repellent properties, therefore can be used in retanning systems for highly water repellent leathers.

ISOPRENE CC is also suitable for retanning resistant to light and heat leathers.

APPLICATIONS

ISOPRENE CC in combination with polymer, synthetic and/or vegetable tanning agents; 3.0 – 4.0%

ISOPRENE CC (% calculated on lowered weight).

After neutralization, during retanning; 2.0 – 4.0%

ISOPRENE CC (% calculated on lowered weight).

The above descriptions correspond to our current level of knowledge and experience. These constitute some advice without commitment and we ask you to adapt them to your particular work.

Unsere Angaben sind unverbindlich; den örtlichen Verhältnissen angepasst und fachrichtig angewendet sind sie zuverlässig.

Les indications ci-dessus n'engagent pas notre responsabilité; elles sont sûres si on les adapte aux conditions locales et si l'application est correctement exécutée.

The foregoing data are given without engagement; they are, however, reliable if applied correctly and adapted to local conditions.