



**TAN PR**

Protein Agent.

#### **COMMERCIAL LABORATORY**

##### **ASA Industria Química Ltda**

453, Adolfo Otto Koch St.

Neighborhood: Das Rosas

Estância Velha/RS

Zip Code: 93602-100

Phone: +55 (51) 3561-9736 / +55 (51) 997-265-261 – Mr. Aldo Stella

E-mail: [asachemical@gmail.com](mailto:asachemical@gmail.com)

[aldost2001@gmail.com](mailto:aldost2001@gmail.com)

#### **CHEMISTRY FEATURE**

<b>Aspect:</b>	Thin powder
<b>Color:</b>	White
<b>Smell:</b>	Characteristic
<b>Solubility:</b>	Soluble
<b>Concentration:</b>	98% +/- 2%
<b>pH (10%):</b>	6,0 +/- 0,5
<b>Charge:</b>	Anionic

#### **PRODUCT CHARACTERISTICS**

**TAN PR** has not tanning effect but it acts stable bonds with the dermic tissue; for that reason gives fine grain with light color.

The leathers retanned with **TAN PR** have excellent fullness particularly in the spongy parts, furthermore it does not degrade dyestuff intensity.

We can easily buff the leather retanned with **TAN PR** to obtain nubuck with pleasant and compact touch, for that property is indicated for suede splits.

We can use **TAN PR** in retanning for waterproof articles because it does not prejudice the impermeability,

We can use **TAN PR** in pH range between 2.5 and 6.5 avoiding precipitation, it is compatible either with anionic or cationic products.

#### **APPLICATIONS**

We suggest to use **TAN PR** in retanning bath before neutralization: as a rule 2 to 4% on the shaved weight.

Furthermore we can use it in fatliquoring step, in this case we add **TAN PR** just before oil mix.

The above descriptions correspond to our current level of knowledge and experience. These constitute some advice without commitment and we ask you to adapt them to your particular work.

Unsere Angaben sind unverbindlich; den örtlichen Verhältnissen angepasst und fachrichtig angewendet sind sie zuverlässig.

Les indications ci-dessus n'engagent pas notre responsabilité; elles sont sûres si on les adapte aux conditions locales et si l'application est correctement exécutée.

The foregoing data are given without engagement; they are, however, reliable if applied correctly and adapted to local conditions.